

Evaluation of poly(lactic acid) and agricultural coproducts as green composite materials

Victoria Finkenstadt, LS Liu, CK Liu, and JL Willett

National Center for Agricultural Utilization Research, ARS, USDA
Eastern Regional Research Center, ARS, USDA

<http://www.ncaur.usda.gov/>

Finkenstadt, NCAUR-USDA, BEPS 2007



Agenda

- Challenge
- Materials
- Preparation
- Evaluation
 - Thermal Properties
 - Mechanical Properties
 - Microscopy
 - Acoustic Emission
- Summary

Finkenstadt, NCAUR-USDA, BEPS 2007

Challenge

- Utilize agricultural "coproducts" from industrial feed streams
 - Pulp from sugar production from beets
 - Pulp from apple orchards & cider production
- Residue from oilseed harvest
 - Pressed seedcake
 - Cellulose, pectin, oil, protein, etc

Finkenstadt, NCAUR-USDA, BEPS 2007

Materials

- Poly(lactic acid) - PLA
 - Commodity plastic
 - Polymerized from lactic acid
 - Lactic acid is a chemical feedstock from the ethanol fermentation process
 - Desirable mechanical properties
 - Biodegradable
- Sugar Beet Pulp
- New Oilseed Crops
 - Cuphea, Lesquerella & Milkweed

Finkenstadt, NCAUR-USDA, BEPS 2007

Alternate Oilseed Crops

- Cuphea
- Lesquerella
- Milkweed
 - Harvested for its floss
 - Seeds contain oil and can be harvested

Finkenstadt, NCAUR-USDA, BEPS 2007

Preparation

- Dry & grind coproduct (300 μm particle size)
- Melt PLA in twin-screw extruder.
- Incorporate coproducts in varying amounts.
- Chop compounded material
- Injection mold each sample into tensile bars
- Condition samples at standard temperature & humidity

Finkenstadt, NCAUR-USDA, BEPS 2007

PLA Composite Materials

- Modify the properties of PLA
 - Fiber reinforcement
- Reduce the cost of the product
 - Fillers
- GREEN

Finkenstadt, NCAUR-USDA, BEPS 2007

PLA Thermal & Mechanical Properties

- Density = 1.25 g/ml
- Molecular Weight = 100K-300K (daltons)
- T_g = 50-80 $^{\circ}\text{C}$
- T_m = 140-180 $^{\circ}\text{C}$

	PLA	PS	PET
Tensile (MPa)	50 - 85	55 - 82	275
Elongation (%)	5 - 10	3 - 40	50 - 150
Modulus (GPa)	2.1 - 3.0	3.0 - 4.0	7.0 - 9.0

Finkenstadt, NCAUR-USDA, BEPS 2007

General results

- SBP
- Cuphea
- Lesquerella
- Apple
- Milkweed
- Plasticized SBP

Finkenstadt, NCAUR-USDA, BEPS 2007

Thermal properties of PLA composites


- T_g = 58 $^{\circ}\text{C}$
- T_m = 155 $^{\circ}\text{C}$ (onset around 141 $^{\circ}\text{C}$)

45%	T_g ($^{\circ}\text{C}$)	T_m ($^{\circ}\text{C}$)
Apple	53	151
Milkweed	54	154
Lesquerella	51	151*
Cuphea	53	149*

* Dual peak


Finkenstadt, NCAUR-USDA, BEPS 2007

Mechanical properties



Finkenstadt, NCAUR-USDA, BEPS 2007


SEM fracture surfaces



Title: sbp 17749-2 4 45
Comment: pulp 45 17749 - 2 sbp fracture s
Date: 11-09-2005 Time: 16:49
Filename: FV20041109


Finkenstadt, NCAUR-USDA, BEPS 2007

Predicted vs. Actual Strength




Finkenstadt, NCAUR-USDA, BEPS 2007

Mechanical properties




Finkenstadt, NCAUR-USDA, BEPS 2007

Mechanical properties



Finkenstadt, NCAUR-USDA, BEPS 2007

Acoustic Emission Milkweed




Finkenstadt, NCAUR-USDA, BEPS 2007

Plasticized SBP


Finkenstadt, NCAUR-USDA, BEPS 2007

AE and TME for pure PLA




Finkenstadt, NCAUR-USDA, BEPS 2007

SEM of PLA fracture surface




Finkenstadt, NCAUR-USDA, BEPS 2007

AE and TME for low pSBP




Finkenstadt, NCAUR-USDA, BEPS 2007

AE and TME for high pSBP




Finkenstadt, NCAUR-USDA, BEPS 2007

SEM for unplasticized & plasticized SBP in PLA



Finkenstadt, NCAUR-USDA, BEPS 2007


Confocal fluorescence & reflection microscopy



PLA – red (reflection)
SBP – green (500-530 nm @ $\lambda=488$ nm)


Finkenstadt, NCAUR-USDA, BEPS 2007

Comparison: SBP-PLA



Finkenstadt, NCAUR-USDA, BEPS 2007

Comparison: plasticized SBP-PLA



Finkenstadt, NCAUR-USDA, BEPS 2007

Results

- SBP-PLA composites behave similar to PLA with cuphea, lesquerella and apple.
- All PLA-fiber composites except milkweed exhibited stronger tensile strength than predicted by the model especially at higher levels of fiber content indicating some level of adhesion between the two phases.
- PLA-milkweed composites show unusual elongation accompanied by stress-cracking or whitening. AE confirms ductile response of composite under stress.

Finkenstadt, NCAUR-USDA, BEPS 2007

Results

- Plasticized SBP-PLA shows ductile behavior and exhibits co-continuous phases.
- It is possible to use agricultural fillers to augment PLA in green composites with some interesting mechanical properties.

Finkenstadt, NCAUR-USDA, BEPS 2007

Next Steps

- Chemically modify agricultural coproduct to promote reinforcement of polymer matrix by adhesion
- Utilize other commodity plastics
 - PCL
 - PEO

Finkenstadt, NCAUR-USDA, BEPS 2007

Acknowledgements

- Mr. Rick Haig
- Brian Jasberg
- Kathy Hornback
- Gary Grose
- Deb Stamm
- ACS Project SEED
 - Dean Stanley
 - Diana Johnson



Finkenstadt, NCAUR-USDA, BEPS 2007